

Titanium additions to MgB_2 conductors

N. E. Anderson, Jr., W. E. Straszheim, S. L. Bud'ko, P. C. Canfield, and D. K. Finnemore

Ames Laboratory, U.S. Department of Energy and Department of Physics and Astronomy

Iowa State University, Ames, Iowa 50011

Raymond J. Suplinskas

Specialty Materials, Inc.

1449 Middlesex Street, Lowell MA 01851

(February 2, 2008)

Abstract

A series of doping experiments are reported for MgB_2 conductors that have been synthesized using doped boron fibers prepared by chemical vapor deposition (CVD) methods. Undoped MgB_2 samples prepared from CVD prepared fibers consistently give critical current densities, J_c , in the range of 500,000 A/cm^2 in low field at 5 K . These values fall by a factor of about 100 as the magnetic field increases to 3 T . For heavily Ti-doped boron fibers where the B/Ti ratio is comparable to 1, there is a substantial suppression of both T_c , superconducting volume fraction, and J_c values. If, however, a sample with a few percent Ti in B is deposited on a carbon substrate and reacted at 1100°C, then T_c is suppressed only a couple of degrees and critical current densities are found to be $J_c \sim 2 - 5 \times 10^6 A/cm^2$ for superconducting layers ranging from 4 – 10 μm thick. These materials show J_c values over 10,000 A/cm^2 at 25 K and 1.3 T .

Typeset using REVTeX

I. INTRODUCTION

Shortly after the discovery of superconductivity in MgB_2 ¹, small wire segments of this compound were prepared by reacting commercial B fibers in a Mg vapor.² Typically these wire segments of pure MgB_2 will carry current densities, J_c , in the range of a few hundred thousand A/cm^2 in self field and 5 K . Fully reacted wire segments were consistently found to show critical current densities, J_c ranging from 100 kA/cm^2 to 500 kA/cm^2 at 5 K and magnetic fields in the range of 0.1 T with a drop by a factor of about 100 as the magnetic field increases to 3 T .

In light of the early success of the Mg vapor diffusion method of sample preparation, a more detailed study of the of the MgB_2 growth process³ was undertaken and has shown that as Mg diffuses into B , a wall of MgB_6 sweeps across the boron fiber, followed by a wall of MgB_4 , and finally a wall of MgB_2 . Energy dispersive spectra (EDS) in a scanning electron microscope (SEM) have shown that the Mg content is rather uniform across any given phase and rises abruptly at the phase boundary. For example, in a region containing both MgB_4 and MgB_2 , the Mg concentration as measured by a 1 μm diameter EDS beam is rather uniform in the MgB_4 region and then rises abruptly at the interface between the MgB_4 and MgB_2 regions within the resolution of the EDS probe of 1 to 2 μm . Then, it is again rather uniform through the MgB_2 region.

Very successful Ti -doping experiments were reported by Zhao et al.⁴ using a solid state reaction method in which powders of Mg , Ti , and B were mixed, pressed, and reacted on an MgO plate in flowing Ar gas. Best results were found for a Ti/Mg ratio of about 0.1 which showed $J_c \sim 2 \times 10^6 A/cm^2$ at 5 K and zero field. Another recent paper by Wang et al.⁵ shows that Y_2O_3 nano-particles can greatly enhance the irreversibility field and J_c performance of MgB_2 in the 3 – 4 T range for samples prepared by a powder-in-tube method. In an alternate approach, Komori et al.⁶ have used a pulsed laser deposition method to prepare 0.5 μm thick films of MgB_2 on a buffered flexible substrate that carry about 100,000 A/cm^2 at 4.2 K and 10 T . These thick films are special because the grain

size is in the nanometer range and J_c remains high out to 10 T .

The purpose of the work reported here is to explore the use of continuous *CVD* methods to dope the MgB_2 phase. It is important to increase both the upper critical field, H_{c2} and the critical current densities in high field by shortening the mean-free-path of the electrons and by adding suitable pinning centers for the superconducting vortices. Impurities tend to suppress the transition temperature, T_c , so it is important to find a trade-off such that the T_c is not reduced too much, but the critical field and critical current are substantially improved. The goal is to find suitable impurities and convenient methods to uniformly disperse them so that the J_c values increase with relatively little suppression of T_c . Emphasis is on chemical vapor deposition processing of the B and vapor diffusion of Mg to form the MgB_2 conductor.

II. EXPERIMENT

A variety of methods have been used to introduce both point defects and small precipitates that will both shorten the electronic mean free path and provide small precipitates. To produce *Ti* impurities, the *Ti* and *B* are co-deposited in a reel-to-reel *CVD* chamber.⁷ Two different substrates were used for the co-deposition of *B* and *Ti*. In some experiments, the substrate is a *W* wire. A 15 μm diameter *W* continuous filament enters the *CVD* chamber in which a mixture of BCl_3 and H_2 are flowing. The conductor is electrically heated to peak temperatures of 1100°C and either pure *B* or *B-Ti* mixtures can be deposited. Titanium is added by bubbling the hydrogen component through $TiCl_4$ held at a temperature near 0°C. The resulting partial pressure of $TiCl_4$ is approximately 2×10^{-3} bar. The *Ti* level is set by the temperature of the $TiCl_4$. In other experiments, the substrate for boron deposition was a 75 μm diameter *SiC* filament coated with several micrometers of glassy carbon known commercially as *SCS-9a*. The *CVD* coated fibers were spooled continuously on emerging from the reactor. After co-deposition of *B* and *Ti*, X-ray patterns show both TiB and TiB_2 in the fibers. The boron is transformed to MgB_2 by immersion in *Mg* vapor as previously reported.² For the *Ti*-doped samples, more details of the structure and *Ti* distribution has

been presented elsewhere.⁸

Critical current values were determined from magnetization hysteresis loops using the Bean Model for cylindrical geometry⁴ by

$$J_c = \frac{1.5\Delta M}{r_o[1 - r_i^3/r_o^3]} \quad 1$$

where ΔM in A/m is the difference in magnetization for field increasing and field decreasing, r_o is the outer radius of the superconductor, and r_i is the inner radius measured in m. Magnetization measurements were made in a Quantum Designs SQUID magnetometer. Both M vs T and the M vs H hysteresis loops were measured sequentially on the same sample.

III. RESULTS AND DISCUSSION

To compare relative performance of various samples, a reference sample of pure MgB_2 sample was made by reacting 100 μm diameter *CVD* boron fibers in a *Ta* container at 950°C for 2 *h*.² The resulting magnetization curve in an applied field of 50 *Oe*, is illustrated in the inset of Fig. 1 and shows the onset of superconductivity at 39.2 *K* and a transition width of a few tenths of a Kelvin. In a separate control measurement, a sample with a pure boron layer 25 μm thick was deposited on a carbon coated *SiC* fiber and reacted in *Mg* vapor as above.² As reported elsewhere,⁸ the J_c vs. H curves of this sample are identical to the sample with pure *B* deposited on W_2B_5 to a thickness of 100 μm . Changing the substrate from W_2B_5 to carbon coated *SiC* and changing the thickness from the 25 μm to 100 μm does not change the J_c vs. H behavior of pure MgB_2 . These results would appear to imply that *C* is not diffusing from the *C* substrate into the MgB_2 during reaction at 950°C for 2 *h* to a level that will have a significant effect on J_c .

A. Heavy *Ti*-doping

Doping with *Ti* has been done at both the 50% and 5% levels. To get a broad perspective, a sample with a high *Ti* level was prepared and converted to *MgB₂* by reacting at 950°C for 2 *h*. This high *Ti* level sample was deposited on a 15 μm *W* substrate similar to the standard pure *MgB₂*, but the diameter was 80 μm rather than 100 μm as in the pure sample. The resulting sample had a *Mg/Ti* ratio of about 1 as determined by the *EDS*. , As shown by the upper curve in the inset of Fig. 1, the low field magnetization has a small diamagnetic drop at ~ 38 *K* and a larger drop in the region of 25 *K*. An energy dispersive X-ray (*EDS*) study in the scanning electron microscope (*SEM*) showed comparable amounts of *Ti* and *Mg* which is consistent with the Meissner screening fraction of about 25 *G* in an external field of 50 *Oe*. As shown by the solid squares of Fig. 1, the pure *MgB₂* sample at 5 *K* shows $J_c \sim 650,000$ *A/cm²* at zero field and $J_c \sim 10,000$ *A/cm²* at 1.5 *T*. At 25 *K*, shown by the solid triangles, $J_c \sim 300,000$ *A/cm²* at zero field and $J_c \sim 10,000$ *A/cm²* at 0.7 *T*. For the *B/Ti* ratio approximately equal to 1 sample, J_c values at 5 *K* are about 200,000 *A/cm²* at zero applied field, but drop below 10,000 *A/cm²* in just a few tenths of a Tesla. This sample clearly has far too much *Ti*.

B. Light *Ti*-doping

Samples with nominally a *Ti/B* ratio of 0.05 were all deposited onto *SiC* substrates coated with glassy carbon so these samples have both *Ti* and possibly some small amount of *C* impurities. A series of *EDS* measurements in the *SEM* show that different samples with boron thicknesses of 4, 6, and 10 μm have somewhat different *Ti* concentrations. These *EDS* studies with a sampling beam diameter of ~ 1 μm indicate that the 4 μm , the 6 μm , and the 10 μm thick samples have *Ti* contents roughly in the ratio of 2 : 1.5 : 1. The 10 μm thick sample has roughly 9% as many *Ti* atoms as *Mg* atoms. The *Ti* and *Mg* peaks are strong and isolated so the result is relatively easy to measure. A systematic study of the

causes for the variation in the Ti content with B thickness has not yet been undertaken, but it is most likely related to the fact that the temperature dependence of Ti is deposition differs from the temperature dependence of B deposition.

Low field magnetization characteristics at 50 Oe are shown in the inset of Fig. 2 for the $4\mu m$ thick sample that has been reacted in Mg vapor at $950^\circ C$ for 1 h and 2 h . The onset of Meissner screening is systematically suppressed to values near 36 K and crosses 50 Oe at about 33 K . For these samples with a few micrometers of superconductor on a $75\ \mu m$ diameter SiC substrate, there is some difficulty determining both the mass of superconductor present. In addition, the reacted samples are not completely straight or really well aligned with the magnetic field so the demagnetizing factor for the sample has some uncertainty. Thus, the absolute magnitude of the $4\pi M$ values could be in error by 30 to 40 percent. All samples were treated in the same manner, however, so sample to sample comparisons are more reliable than the absolute value of the magnetization. The pure MgB_2 sample of Fig. 2 and Fig. 3 is a $100\ \mu m$ diameter boron fiber on a $15\ \mu m$ diameter W_2B_5 substrate that has been reacted in Mg vapor at $950^\circ C$ for 2 h .

The semi-logarithmic plot of J_c vs field for these two samples at 5 K are a factor of 8 higher than pure MgB_2 at low field. Both the 1 h reaction and the 2 h reaction samples have essentially the same J_c dropping from about $5,000,000\ A/cm^2$ at 0.1 T to about $50,000\ A/cm^2$ at 3 T as shown in Fig. 2. Above 2 T , the improvement is very substantial.

Because short reaction times are usually desirable in any commercial process, a series of samples ranging in thickness from $4 - 10\ \mu m$ were deposited on a C substrate and reacted at $1100^\circ C$ for 15 min . The transition temperature again is suppressed to about 35 K as shown in the inset of Fig. 3. With these reaction conditions, the value of J_c in zero applied field systematically drops from about $4,000,000\ A/cm^2$ for a $4\ \mu m$ thick layer to about $2,000,000\ A/cm^2$ for a $10\ \mu m$ thick layer as shown in Fig. 3. If these data are plotted on a semi-logarithmic scale to emphasize the lower J_c values at high magnetic field, this trend with thickness is reversed. In the region of 3 T , the $10\ \mu m$ thick sample shown by the solid triangles in Fig. 4 carries more than $100,000\ A/cm^2$ and the $4\ \mu m$ thick sample

shown by the solid squares carries about $10,000 \text{ A/cm}^2$. If the temperature is raised to 25 K , the $10 \text{ }\mu\text{m}$ thick sample has $J_c \sim 600,000 \text{ A/cm}^2$ in zero applied field and about $J_c \sim 10,000 \text{ A/cm}^2$ at 1.3 T as shown on Fig. 4. .

C. Optimization of *Ti*-doped samples

Optimization of the J_c performance as a function of reaction times was performed at two different temperatures of 1100°C and 950°C . Here, the 25 K data for J_c are shown because this is the most likely operating temperature. As shown in Fig. 5a, the optimum reaction time at 1100°C is in the range of 15 to 30 minutes, and the samples show $J_c \sim 10,000 \text{ A/cm}^2$ at 1.2 T . As shown in Fig. 5b, the optimum reaction time at 950°C is about 2 h , and the samples show $J_c \sim 10,000 \text{ A/cm}^2$ at 1.3 T . Our assumption has been that the degradation of J_c and T_c at long times may arise from the diffusion of carbon from the substrate into the MgB_2 . It is difficult, however, to determine the carbon content in these layers of MgB_2 that are 4 to $10 \text{ }\mu\text{m}$ thick and are on a C substrate. The *EDS* carbon peak is a shoulder on the B peak and is small compared to the *Ti* peak for all temperature and times studied for the $10 \text{ }\mu\text{m}$ thick sample. If you were very optimistic about the data interpretation, the carbon shoulder may grow to a value of 10 percent of the titanium peak for the sample reacted at 1100°C and 45 min where there is significant degradation of J_c . This degradation of J_c , however, may also come from a rearrangement of the *Ti* as well. Further work needed to improve the determination of the carbon content and the causes for the observed changes in J_c of the superconductor.

IV. CONCLUSIONS

Titanium impurities co-deposited with the boron in a *CVD* process is a very effective method to raise the critical current performance in the range 3 T at 5 K and in the range of 1.3 T at 25 K . The value of T_c is suppressed only 2 K or 3 K and there is a very substantial enhancement of J_c . These *CVD* methods are an effective way to distribute the *Ti* impurities

and can be used to produce conductors with J_c values in the range of $10,000\text{ A/cm}^2$ at 25 K and 1.3 T .

V. ACKNOWLEDGMENTS

Work is supported by the U.S. Department of Energy, Basic Energy Sciences, Office of Science, through the Ames Laboratory under Contract No. W-7405-Eng-82.

REFERENCES

- ¹ J. Nagamatsu, N. Nakagawa, T. Muranaka, Y. Zenitani, and J. Akimitsu, *Nature* **410**, 63 (2001).
- ² P. C. Canfield, D. K. Finnemore, S. L. Bud'ko, J. E. Ostenson, G. Lapertot, C. E. Cunningham, and C. Petrovic, *Phys. Rev. Lett.* **86**, 2423 (2001).
- ³ C. E. Cunningham, C. Petrovic, G. Lapertot, S. L. Bud'ko, F. Laabs, W. Straszheim, D. K. Finnemore, and P. C. Canfield, *PhysicaC* **353**, 5 (2001).
- ⁴ Y. Zhao, Y. Feng, C. H. Cheng, L. Zhou, Y. Wu, T. Machi, Y. Fudamoto, N. Koshizuka, and M. Murakami, *Appl. Phys. Lett.* **79**, 1154 (2001).
- ⁵ J. Wang, Y. Bugoslavsky, A. Ferenov, L. Cowey, A. D. Caplin, L. F. Cohen, J. L. MacManus Driscoll, L. D. Cooley, X. Song, and D. C. Larbalestier, preprint.
- ⁶ K. Komori, K. Kawagishi, Y. Takano, S. Arisawa, H. Kumakura, M. Fukutomi, and K. Togano, *Appl. Phys. Lett.* **81**, 1047 (2002).
- ⁷ R. J. Suplinskas and J. V. Marzik, "Boron and Silicon Carbide Filaments," in Handbook of Reinforcements for Plastics, J. V. Milewski and H. S. Katz, ed., Van Nostrand Reinhold, New York, (1987).
- ⁸ D. K. Finnemore, W. E. Straszheim, S. L. Bud'ko, P. C. Canfield, N. E. Anderson, and R. J. Suplinskas, *Physica C* **385**, 278 (2003).

FIGURES

FIG. 1. Values of J_c for pure MgB_2 and a sample with a Ti/Mg ratio of about 1. The inset shows magnetization curves in 50 Oe .

FIG. 2. Semi-logarithmic plot of values of J_c for Ti -doped MgB_2 reacted at $950^\circ C$. The inset shows magnetization vs. temperature data in the $30 - 40 K$ range for these samples in 50 Oe . At low T , the data level out at about $100 - 150 G$.

FIG. 3. Thickness variation of J_c for samples doped with both Ti and C and reacted at $1100^\circ C$. Inset shows magnetization for these samples in 50 Oe . At low T , the data level out at about $75 - 100 G$.

FIG. 4. Semi-logarithmic plot to compare the high field and low field variation in J_c with thickness. For the $10 \mu m$ sample, the $5 K$ data are shown by the solid triangles with the point up, and the $25 K$ data are shown by the solid triangles with the point down.

FIG. 5. Performance characteristics for $10 \mu m$ thick samples reacted at (a) $1100^\circ C$ and (b) $950^\circ C$.

This figure "Fig1ti.JPG" is available in "JPG" format from:

<http://arXiv.org/ps/cond-mat/0302245v1>

This figure "Fig2ti.JPG" is available in "JPG" format from:

<http://arXiv.org/ps/cond-mat/0302245v1>

This figure "fig3ti.JPG" is available in "JPG" format from:

<http://arXiv.org/ps/cond-mat/0302245v1>

This figure "Fig4ti.JPG" is available in "JPG" format from:

<http://arXiv.org/ps/cond-mat/0302245v1>

This figure "Fig5ati.JPG" is available in "JPG" format from:

<http://arXiv.org/ps/cond-mat/0302245v1>

This figure "Fig5bti.JPG" is available in "JPG" format from:

<http://arXiv.org/ps/cond-mat/0302245v1>